



PRODUCT DESCRIPTION: V-2879Universal Acrylic Modified Gray Primer is formulated with corrosion resistant resins, and rust inhibitive additives. This non-sanding primer, after proper curing is suitable for use under a wide range of high performance topcoats, including epoxy, urethane, and acrylic enamels. This primer has superior adhesion and is lead and chromium free.

INTENDED USES: Shop coating or field priming weather-exposed structural and miscellaneous steel tanks, machinery, and equipment to be top coated with most oil, alkyd, or latex topcoats. Do not use on galvanized metal or immersion service. For optimum performance a topcoat is required for exterior exposures.

SURFACE PREPARATIONS: For best results, it is important that all surface contaminants, such as moisture, oil, dirt, rust, and mill scale be removed before application of this primer. V-2879 universal acrylic gray primer can be applied to either blasted, hand, or power tool cleaned steel. A minimum of SSPC-2 hand tool cleaning required.

PHYSICAL INFORMATION

COLOR: GRAY GLOSS LEVEL: FLAT VOLUME SOLIDS: 68%

RECOMMENDED DRY FILM THICKNESS: 1.5-2.0 MILS THEORETICAL COVERAGE: 350-400 SQ FT PER GALLON

METHOD OF APPLICATION: AIRLESS SPRAY, AIR SPRAY, BRUSH, AND ROLLER

DRYING TIME @ 72 F

TO TOUCH: 15-30 MINUTES TO HANDLE: 30-90 MINUTES TO RECOAT: 4-12 HOURS

REGULATORY DATA

FLASHPOINT: 80 F

PRODUCT WEIGHT: 10.38 LB

MATERIAL VOC: 3.22 POUNDS PER GALLON / 387 GRAMS PER LITER COATING VOC: 3.22 POUNDS PER GALLON / 387 GRAMS PER LITER



TECHNICAL DATA SHEET MIXING: This material is a one-component coating and should always be mixed thoroughly with a power agitator before

application.

MIX RATIO: Not applicable

WORKING POT LIFE: Not applicable

AIRLESS SPRAY: Recommended Tip range 15-17 thou (0.38-0.43 mm)

Total output fluid pressure at spray tip not less

than 2,500 p.s.i.

DeVilbiss AIR SPRAY: Recommended MBC or JGA Gun

(Pressure Pot) Air Cap 704

> Tip E

BRUSH: Suitable Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

ROLLER: Suitable Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

THINNER: Xylene Do not thin more than allowed by local

environmental legislation.

CLEANER: Xylene

WORK STOPPAGES: Thoroughly flush all equipment with xylene. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and / or viscosity increase of the material after storage. Material should be filtered prior to use.

CLEAN UP: Clean all equipment immediately with xylene. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations / legislation.

SYSTEM COMPATIBILITY

The following topcoats are recommended for V-2879 universal gray primer.

Alkyds

Silicone Alkyds

Latex

Acrylic Enamels

Urethanes

Epoxies_

SHIPPING & STORAGE

NUMBER OF COMPONENTS: 1

PACKAGED IN: 55-Gallon Drums, 5 Gallon Pails, and 1 Gallon Cans STORAGE TEMPERATURE: Minimum 20 F. Maximum 110 F.

